

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 132 634 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
12.09.2001 Bulletin 2001/37

(51) Int Cl.7: **F16C 33/20**

(21) Application number: **00111970.0**

(22) Date of filing: **16.06.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **08.03.2000 JP 2000063838**

(71) Applicant: **OILES CORPORATION**
Minato-ku, Tokyo (JP)

(72) Inventors:
• **Yanase, Sumihide**
Ebina-shi, Kanagawa-ken (JP)
• **Nakamaru, Takashi**
Aikou-gun, Kanagawa-ken (JP)

(74) Representative: **HOFFMANN - EITLE**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(54) **Resin composition for sliding member, and sliding member produced therefrom**

(57) A resin composition for a sliding member of the present invention comprises 5 to 40% by weight of barium sulfate; 1 to 30% by weight of a phosphate; 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a polyphenylene sulfone resin; and the bal-

ance of a polytetrafluoroethylene resin, and a sliding member produced from the resin composition.

Such a resin composition suitable for producing a sliding member capable of exhibiting a stable low friction coefficient and an extremely low wear amount under dry frictional condition, or under oil-immersed or oil-lubricated condition.

EP 1 132 634 A2

Description

BACKGROUND OF THE INVENTION

[0001] The present invention relates to a resin composition for a sliding member, and a sliding member produced from the resin composition, and more particularly, to a resin composition suitable for producing a sliding member capable of exhibiting a stable low friction coefficient and an extremely low wear amount under dry frictional condition, or under oil-immersed or oil-lubricated condition, and a sliding member capable of exhibiting a stable low friction coefficient and an extremely low wear amount under dry frictional condition, or under oil-immersed or oil-lubricated condition, which is produced from such a resin composition.

[0002] Hitherto, since polytetrafluoroethylene resins (hereinafter simply referred to as "PTFE resin") have not only excellent self-lubricating properties and low friction coefficient, but also chemical resistance and heat resistance, these resins have been used generally for sliding members such as bearings.

[0003] However, since the sliding member made of the PTFE resin solely is poor in the wear resistance and load carrying capacity, such a drawback is compensated, for example, by (a) incorporating a solid lubricant such as graphite and molybdenum disulfide, and/or a reinforcing material such as glass fibers and carbon fibers into the PTFE resin, (b) filling the PTFE resin in the pores of a porous sintered metal layer lined by a steel backing plate and coating the surface of the sintered metal layer therewith, or (c) filling the PTFE resin in the meshes of a metal mesh and coating the surface of the metal mesh therewith, depending on the applications of the sliding member.

[0004] The sliding members formed by the method (b) have been known as a so-called multi-layered sliding member, and described, for example, in U.S. Patent No. 2,689,380 (1954) and Japanese Patent Publications (KOKOKU) No. 31-2452(1956), No. 39-16950(1964) and No. 41-1868(1966). The multi-layered sliding members described in these publications have been produced by filling the PTFE resin or the PTFE resin containing a filler composed of lead or a lead oxide in the pores of a porous sintered metal layer lined by a steel backing plate, and coating the surface of the sintered metal layer therewith.

[0005] The sliding members formed by the method (c) are described, for example, in Japanese Patent Publication (KOKOKU) No. 55-23740(1980). In the publication, there is disclosed as a sliding member a self-lubricating lining foil comprising a metal wire fabric, a fluoro-plastic and a reinforcing material of inorganic fiber.

[0006] In the sliding members described above, fillers have been selectively used according to various different working conditions, for example, under dry frictional condition, oil-immersed condition or oil-lubricated condition, but these sliding members fail to fully satisfy requirements under all of the working conditions.

[0007] Further, in a PTFE resin composition for sliding member, it has been attempted to use therein fillers for engineering plastics, for example, graphite, molybdenum disulfide or other metal sulfides, metal oxides, or inorganic fibers such as glass fibers and carbon fibers. Although these fillers contribute to the improvement of the wear resistance of the resin layer, the fillers tend to cause such a problem that the use thereof adversely affects the low-friction property inherent to the PTFE resin. In particular, lead have been widely used as a filler in these resins to improve the wear resistance of a sliding layer. However, for secondary reasons such as recent environmental pollution and public nuisance, the use of lead must be avoided.

[0008] As a result of the present inventors' earnest studies, it has been found that by filling in the pores of a porous sintered metal layer formed on a steel backing plate and coating the surface of the sintered metal layer with a resin composition prepared by blending PTFE with a specific amount of barium sulfate, a phosphate, a polyimide resin, a phenol resin-calcined product or a polyphenylenesulfone resin, or by filling in the meshes of a metal mesh and coating the surface of the metal mesh with a resin composition prepared by blending PTFE with a specific amount of barium sulfate, a phosphate, a polyimide resin, a phenol resin-calcined product or a polyphenylene sulfon resin, the obtained sliding member can exhibit excellent friction and wear characteristics under dry frictional condition, or under oil-immersed or oil-lubricated condition. The present invention has been attained based on this finding.

SUMMARY OF THE INVENTION

[0009] An object of the present invention is to provide a resin composition for a sliding member capable of exhibiting excellent friction and wear characteristics under various different working conditions, i.e., under dry frictional condition, oil-immersed condition or oil-lubricated condition.

[0010] Another object of the present invention is to provide a sliding member capable of exhibiting excellent friction and wear characteristics under various different working conditions, i.e., under dry frictional condition, oil-immersed condition or oil-lubricated condition, which are produced using the resin composition.

[0011] To accomplish the aims, in a first aspect of the present invention, there is provided a resin composition for a sliding member comprising 5 to 40% by weight of barium sulfate; 1 to 30% by weight of a phosphate; 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a

polyphenylene sulfone resin; and the balance of a polytetrafluoroethylene resin. In a second aspect of the present invention, there is provided a sliding member comprising:

a substrate comprising a steel backing plate and a porous sintered metal layer formed on said steel backing plate, or comprising a metal mesh; and
a resin composition applied to pores or meshes and a surface of said substrate, comprising 5 to 40% by weight of barium sulfate, 1 to 30% by weight of a phosphate, 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a polyphenylene sulfone resin and the balance of a polytetrafluoroethylene resin.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012]

Fig. 1 is a cross-sectional view illustrating an example of a sliding member according to the present invention;
Fig. 2 is a plan view of an expanded metal as a substrate;
Fig. 3 is a cross-sectional view illustrating an example of a sliding member according to the present invention, wherein the expanded metal as shown in Fig. 2 is used as a substrate; and
Fig. 4 is a cross-sectional view illustrating an example of a sliding member according to the present invention,

wherein a woven wire mesh is used as a substrate.

DETAILED DESCRIPTION OF THE INVENTION

[0013] The present invention will be described in detail below.

[0014] First, the resin composition for a sliding member according to the present invention is explained.

[0015] As the PTFE resin as a main component of the resin composition according to the present invention, there can be used fine powder, for example, commercially available products such as "Teflon 6CJ" (tradename, produced by Mitsui duPont Fluorochemical Co., Ltd), "Polyflon F201" (tradename, produced by Daikin Kogyo Co., Ltd), and "Fluon CD-076" and "Fluon CD-1" (tradenames, both produced by Asahi Glass Co., Ltd).

[0016] There may be used a PTFE resin composition comprising the above fine powder and a molding powder, for example, "Teflon 7AJ" (tradename, produced by Mitsui duPont Fluorochemical Co., Ltd.) which is blended therewith in an amount of not more than 20% by weight based on the resin composition.

[0017] The content of the PTFE resin in the resin composition is the balance (remainder) which is calculated by subtracting an amount of the filler such as barium sulfate, phosphate, polyimide resin, phenol resin-calcined product, polyphenylene sulfone resin, graphite and molybdenum disulfide from the total amount of the resin composition. The content of the PTFE resin is preferably 50 to 93 % by weight.

[0018] When the barium sulfate (BaSO_4) is incorporated as a filler in the PTFE resin, the obtained resin composition is free from drawbacks of the conventional sliding member made of the PTFE resin singly, such as deteriorated wear resistance and load carrying capacity, and can be considerably enhanced in the wear resistance and load carrying capacity. The effects by the addition of barium sulfate are more remarkably exhibited especially under low-load working conditions of the sliding member.

[0019] As the barium sulfate (BaSO_4), there may be used either precipitated-type barium sulfate or baryte-type barium sulfate. Such barium sulfate is easily available, for example, from Sakai Chemical Industry Co., Ltd. The average particle size of barium sulfate is usually not more than 10 μm , preferably from 1 to 5 μm . The amount of the barium sulfate blended is usually from 5 to 40% by weight, preferably 10 to 30% by weight, more preferably 15 to 25% by weight based on the weight of the resin composition.

[0020] When the amount of the barium sulfate blended is less than 5% by weight, it is difficult to achieve the above effects of improving an wear resistance and a load carrying capacity of the resin composition. On the contrary, when the amount of the barium sulfate blended is more than 40% by weight, there is a tendency to lower a mechanical strength and a load carrying capacity.

[0021] The phosphate as the filler for the resin composition according to the present invention does not exhibit a lubricating property, unlike solid lubricants such as graphite and molybdenum disulfide. However, when the phosphate is blended with the PTFE resin, the phosphate exhibits an effect of promoting a lubricating film-forming property of the PTFE resin to the surface of a mating member (sliding surface), thereby enhancing sliding characteristics of the sliding member such as low-friction property and wear resistance.

[0022] As the phosphate used in the present invention, there may be exemplified metal salts such as metal secondary phosphate, metal tertiary phosphate, metal pyrophosphate, metal phosphite, metal metaphosphate and a mixture there-

of. Among these phosphates, metal secondary phosphate, metal tertiary phosphate, metal pyrophosphate are preferred. As the salt-forming metal, alkali metals and alkali earth metals are preferred, and lithium (Li) and calcium (Ca) are more preferred.

[0023] Specific examples of the phosphates may include trillithium phosphate (Li_3PO_4), lithium hydrogen phosphate (Li_2HPO_3), lithium pyrophosphate ($\text{Li}_4\text{P}_2\text{O}_7$), tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$), calcium pyrophosphate ($\text{Ca}_2\text{P}_2\text{O}_7$), calcium hydrogen phosphate (CaHPO_4) and the like. Among these phosphates, calcium pyrophosphate ($\text{Ca}_2\text{P}_2\text{O}_7$) is preferred.


[0024] Even when only a small amount, for example, 1% by weight of the phosphate based on the weight of the resin composition is blended in the PTFE resin, the above effect of promoting the formation of lubricating film can be observed, and maintained until the amount of the phosphate blended reaches 30% by weight. However, when the amount of the phosphate blended exceeds 30% by weight based on the weight of the resin composition, a too large amount of lubricating film may be formed on the surface of the mating member, thereby rather causing deterioration in wear resistance of the sliding member. Therefore, the amount of the phosphate blended is usually 1 to 30% by weight, preferably 5 to 25% by weight, more preferably 10 to 20% by weight based on the weight of the resin composition. When the amount of the phosphate blended is less than 1% by weight, it is difficult to obtain the effect of promoting the formation of lubricating film.

[0025] When the polyimide resin, phenol resin-calcined product or polyphenylene sulfone resin are blended as a filler in the resin composition according to the present invention, these fillers contribute to enhancement of wear resistance and heat resistance of the sliding member obtained therefrom. The effect of enhancing the wear resistance is more remarkably exhibited when the sliding member is used under high-load working condition. These fillers compensates the drawback observed when the sliding member containing the barium sulfate solely as a filler is used under the high load working condition. Thus, when the above polyimide resin, phenol resin-calcined product or polyphenylene sulfone resin is blended together with barium sulfate in the resin composition, the obtained sliding member can be used under more extensive working conditions.


[0026] As the polyimide resins, there may be used aromatic polyimide resins such as "PB4 Polyimide" (tradename, produced by Lenzing AG.) and thermosetting polyimide resins such as "Bismaleimide" (tradename, produced by Ciba Geigy AG.), "Techmigt" (tradename, produced by Mitsui Kagaku Co., Ltd.) and "Carbodiimide" (tradename, produced by Nisshin Boseki Co., Ltd.).

[0027] As the phenol resin-calcined products, there may be exemplified products obtained by carbonizing (calcining) phenol/formaldehyde resin particles at a high temperature of from 400 to 2,200°C in an inert atmosphere, for example, "Bellpearl C-800" and "Bellpearl C-2000" (tradenames, both produced by Kanebo Co., Ltd.).

[0028] As the polyphenylene sulfone resins, there may be exemplified polymers composed mainly of a repeating unit represented by the following general formula (I). Further, it is preferred that in the repeating unit (I), a structural unit represented by the following formula (II) is contained in an amount of not less than 60%.



wherein X is 0, 1 or 2.



[0029] Specific examples of the polyphenylene sulfone resins may include "Ceramers" (tradename, produced by Hoechst AG.) and the like.

[0030] The polyimide resins, phenol resin-calcined products and polyphenylene sulfone resins may be used singly or in the form of a mixture of any two or more thereof. The amount of polyimide resin, calcined product of phenol resin or polyphenylene sulfone resin blended is usually 1 to 10% by weight, preferably 1 to 7% by weight, more preferably

2 to 5% by weight based on the weight of the resin composition.

[0031] When the amount of the polyimide resins, phenol resin-calcined products or polyphenylene sulfone resin blended is less than 1% by weight, it is difficult to achieve the above effects of improving wear resistance and heat resistance of the resin composition.

[0032] For the purpose of further enhancing the wear resistance, the resin composition of the present invention may further contains, in addition to the above components, a solid lubricant selected from graphite and molybdenum disulfide in an amount of usually not more than 5% by weight, preferably 0.5 to 3% by weight, more preferably 0.5 to 2% by weight based on the weight of the resin composition.

[0033] Next, the sliding member according to the present invention and the process for producing the sliding member will be explained.

[0034] First, the multi-layered sliding member (I) using a substrate comprising a backing plate made of thin steel plate and a porous sintered metal layer lined by the backing plate, and the process for the production of such a multi-layered sliding member are explained.

[0035] As the backing plate of the substrate, there may be used a general structural rolled steel plate. As the steel plate, a continuous steel strip provided in the form of a coiled hoop material is preferred, though not limited thereto. However, other steel strip materials cut into an appropriate length may also be used in the present invention. These steel strips may be copper-plated or tin-plated, if required, in order to improve the corrosion resistance thereof.

[0036] As the metal powder for forming the porous sintered metal layer, there may be suitably used copper alloys capable of passing through about 100 mesh sieve, such as bronze, lead bronze and phosphor bronze, which are inherently excellent in friction and wear characteristics. However, other metal powders, for example, those of aluminum alloys or iron may be used depending upon aimed applications. The metal powder may have any particle shape such as massive shape, spherical shape or other irregular shapes. There are required that the metal powder particles of the porous sintered metal layer are strongly bonded to each other and the sintered metal layer is strongly bonded to the steel strip backing plate, and that the sintered metal layer has predetermined thickness and porosity. The thickness of the porous sintered metal layer is usually 0.15 to 0.40 mm, preferably 0.2 to 0.3 mm. The porosity of the porous sintered metal layer is usually not less than 10% by volume, preferably 15 to 40% by volume.

[0037] A resin composition having a wettability can be obtained by mixing a PTFE resin powder with the above fillers and then admixing under stirring a petroleum-based solvent into the resultant mixture. The PTFE resin and the fillers are mixed at a temperature not more than the room-temperature transition point (19°C) of the PTFE resin, preferably from 10 to 18°C. Further, the resultant mixture and the petroleum-based solvent are also mixed under stirring at the same temperature as described above. By such a temperature condition, fibrillation of the PTFE resin can be inhibited, thereby obtaining a homogeneous mixture.

[0038] As the petroleum-based solvent, there may be used naphtha, toluene, xylene, an aliphatic solvent or a mixed solvent of an aliphatic solvent and a naphthenic solvent. The amount of the petroleum-based solvent used is from 15 to 30 parts by weight based on 100 parts by weight of a mixture of the PTFE resin powder and the fillers. When the amount of the petroleum-based solvent used is less than 15 parts by weight, the extensibility of the resin composition having a wettability is poor in the filling and covering step of the porous sintered metal layer as described later with the resin composition, so that uneven filling and covering of the porous sintered metal layer with the resin composition tends to occur. On the other hand, when the amount of the petroleum-based solvent used exceeds 30 parts by weight, the filling and covering operation becomes difficult, and the uniformity of the thickness of the resin composition applied and the adhesion between the resin composition and the porous sintered metal layer are deteriorated.

[0039] The sliding member (I) according to the present invention is produced by the following steps (a)-(d).

(a) A resin composition having a wettability is spread over a porous sintered metal layer formed on a thin steel backing plate, and rolled to fill the resin composition into pores of the porous sintered metal layer and simultaneously coat the surface of the porous sintered metal layer to form a coating layer of the resin composition having a uniform thickness thereon. In this step, the thickness of the coating layer is from 2 to 2.5 times the thickness of the resin layer required for final products. The filling of the resin composition into pores of the porous sintered metal layer is substantially accomplished during this step.

(b) The backing plate thus treated in the step (a) is held in a drying furnace heated to a temperature of from 200 to 250°C for several minutes to remove the petroleum-based solvent. Then, the dried resin composition is rolled under a pressure of 300 to 600 kgf/cm² to obtain the predetermined thickness of the coating layer.

(c) The backing plate thus treated in the step (b) is introduced into a heating furnace, and heated at a temperature of from 360 to 380°C for a period between several minutes and ten and several minutes to sinter the resin composition. Then, the backing plate is taken out of the furnace and rolled again to correct the size.

(d) The backing plate subjected to the correction in the step (c) is cooled (air-cooled or naturally-cooled), and then subjected to correction of waviness or the like of the backing plate, if required, thereby obtaining an aimed sliding member.

[0040] The sliding member thus obtained by the steps (a) through (d), comprises the porous sintered metal layer having a thickness of 0.10 to 0.40 mm, and the coating layer composed of the resin composition having a thickness of 0.02 to 0.15 mm. The thus obtained sliding member is cut into an appropriate size, and used as a flat sliding plate, or as a cylindrical winding bush by bending.

[0041] Next, the sliding member (II) of the present invention using a metal mesh as a substrate and the process for producing such a sliding member are explained.

[0042] As the metal mesh as a substrate, there may be used (i) an expanded metal produced by inserting a thin metal plate between a stationary lower die equipped with a linear blade and a movable upper die equipped with a wave-shaped, trapezoid or triangular blade, in a direction perpendicular or inclined to the linear blade of the stationary lower die, and vertically reciprocating the movable upper die to notch the thin metal plate and simultaneously spread the notched plate, thereby forming meshes regularly arranged in rows on the plate, (ii) a woven wire mesh formed by weaving fine metal wires as warp and weft, and (iii) a knitted wire mesh formed by knitting fine metal wires.

[0043] As the preferable expanded metal, there may be used those produced by processing a thin metal plate having a thickness of 0.3 to 2 mm into an expanded metal form having a side (strand) length of 0.1 to 1.5 mm and a thickness of 0.1 to 1.0 mm. As the preferable woven or knitted wire mesh, there may be used those produced by weaving or knitting fine metal wires having a diameter of 0.1 to 0.5 mm into a net having 10 to 100 meshes.

[0044] As the metal materials constituting the expanded metal or woven or knitted wire mesh, there may be suitably used thin metal plates or fine wires made of stainless steel, copper, phosphor bronze, bronze, iron or the like.

[0045] The sliding member (II) according to the present invention can be produced through the following steps (a') to (c'). In the production of the sliding member (II), the same resin composition as described above for the production of the sliding member (I) is used.

(a') The resin composition is spread over the expanded metal or the woven or knitted wire mesh, and rolled to fill the meshes of the metal mesh with the resin composition and simultaneously coat the surface of the metal mesh, thereby forming a coating layer having a uniform thickness thereon. In this step, the thickness of the thus formed coating layer is from 2 to 2.5 times the thickness of the resin layer required for final products.

(b') The metal mesh treated in the step (a') is held in a drying furnace heated to a temperature of 200 to 250°C for several minutes to remove the petroleum-based solvent. Then, the dried resin composition is rolled under a pressure of 300 to 600 kgf/cm² to obtain a predetermined thickness.

(c') The metal mesh treated in the step (b') is introduced into a heating furnace, and heated at a temperature of 360 to 380°C for a period between several minutes and ten and several minutes to sinter the resin composition. Then, the metal mesh is taken out of the furnace and rolled again to correct the size, thereby obtaining an aimed sliding member.

[0046] In the sliding member obtained through the steps (a') to (c'), the thickness of the coating layer composed of the resin composition formed on the surface of the metal mesh is usually from 0.05 to 1.0 mm. The thus obtained sliding member is cut into an appropriate size and used as a flat sliding plate or as a cylindrical winding bush by bending.

[0047] As described above, in accordance with the present invention, there is provided a sliding member capable of exhibiting excellent sliding characteristics such as stable low friction coefficient and extremely low wear amount under various different working conditions, for example, under dry frictional condition, oil-immersed condition or oil-lubricated condition.

EXAMPLES

[0048] The present invention will be described in more detail below with reference to examples. However, these examples are merely illustrative and not intended to limit the invention thereto.

[0049] In the following examples, the sliding characteristics of the sliding member (I) were evaluated by the following test methods (1) to (4), and those of the sliding member (II) were evaluated by the test method (2).

Thrust Test (1):

[0050] A friction coefficient and wear amount were measured under the conditions described in Table 1 below. Then, the friction coefficient was indicated by the value measured upon a stable condition during the period of from one hour after the start of the test up to the completion of the test. Further, the wear amount was indicated by the amount of dimensional change of the sliding surface after a test time of 8 hours.

EP 1 132 634 A2

Table 1

Sliding speed	20 m/min.
Load	20 kgf/cm ²
Test time	8 hrs.
Lubrication	non-lubrication
Mating member	Carbon steel for mechanical structural use (S45C)

Thrust Test (2):

[0051] A friction coefficient and wear amount were measured under the conditions described in Table (2) below. Then, the friction coefficient was indicated by the value measured upon a stable condition during the period of from one hour after the start of the test up to the completion of the test. Further, the wear amount was indicated by the amount of dimensional change for the sliding surface after a test time of 8 hours.

Table 2

Sliding speed	10 m/min.
Load	100 kgf/cm ²
Test time	8 hrs.
Lubrication	non-lubrication
Mating member	Carbon steel for mechanical structural use (S45C)

Reciprocating Slide Test (3):

[0052] A friction coefficient and wear amount were measured under the conditions described in Table (3) below. Then, the friction coefficient was indicated by the value measured upon a stable condition during the period of from one hour after the start of the test up to the completion of the test. Further, the wear amount was indicated by the amount of dimensional change for the sliding surface after a test time of 8 hours.

Table 3

Sliding speed	5 m/min.
Load	50 kgf/cm ²
Test time	8 hrs.
Lubrication	Lubricating oil (ATF-DII produced by Idemitsu Kosan Co., Ltd.)
Mating member	Carbon steel for mechanical structural use (S45C)

Reciprocating Slide Test (4):

[0053] A friction coefficient and wear amount were measured under the conditions described in Table (4) below. Then, the friction coefficient was indicated by the value measured upon a stable condition during the period of from one hour after the start of the test up to the completion of the test. Further, the wear amount was indicated by the amount of dimensional change for the sliding surface after a test time of 8 hours.

Table 4

Sliding speed	5 m/min.
Load	100 kgf/cm ²
Test time	8 hrs.
Lubrication	Lubricating oil (ATF-DII produced by Idemitsu Kosan Co., Ltd.)
Mating member	Carbon steel for mechanical structural use (S45C)

Examples 1 to 20 and Comparative Examples 1 to 3:

[0054] In the following examples and comparative examples, "Polyflon F201" (tradename, produced by Daikin Kogyo Co., Ltd) was used as the PTFE resin, and a mixed solvent of an aliphatic solvent and a naphthenic solvent "Exxsol" (tradename, produced by Exxon Chemical Co., Ltd) was used as the petroleum-based solvent.

[0055] First, the PTFE resin and each of the fillers shown in Tables 5 to 10 were charged into a Henschel mixer, and mixed under stirring. 20 parts by weight of the petroleum-based solvent was blended with 100 parts by weight of the resultant mixture, and mixed at a temperature (15°C) lower than the room-temperature transition point of the PTFE resin, to obtain a resin composition.

[0056] The thus obtained resin composition was spread over a porous sintered metal (bronze) layer (thickness: 0.25 mm) formed on a thin steel backing plate (thickness: 0.70 mm), and rolled for filling the resin composition into pores of the porous sintered metal layer and coating the surface of the porous sintered metal layer therewith so as to form a resin composition layer having a thickness of 0.25 mm, thereby obtaining a multi-layered plate. The thus obtained multi-layered plate was held in a hot-air drying furnace heated to 200°C for 5 minutes to remove the solvent. Then, the dried multi-layered plate was rolled under a pressure of 400 kgf/cm² to form a resin composition layer having a thickness of 0.10 mm on the sintered metal layer.

[0057] The multi-layered plate thus pressure-treated was then introduced into a heating furnace, and heated at 370°C for 10 minutes to sinter the resin composition. Subsequently, the plate was rolled again to correct the size and waviness of the plate, thereby obtaining a multi-layered sliding member. After completion of the correction, the multi-layered sliding member was cut into a rectangular test piece having each side length of 30 mm.

[0058] Fig. 1 shows a cross-sectional view of the thus obtained multi-layered sliding member. In Fig. 1, reference numeral 1 denotes a steel backing plate; 2 denotes a porous sintered metal layer lined by the steel backing plate; and 3 denotes a coating layer (sliding layer) formed by filling pores of the porous sintered metal layer 2 with the resin composition and coating the surface of the sintered metal layer therewith.

[0059] The results of the thrust tests (1) and (2) for each of the obtained sliding members are shown in Tables 5 to 10.

[0060] In the tables, the amounts of respective components blended are indicated by "% by weight". Further, "Bellpearl C-2000" (tradename, produced by Kanebo Co., Ltd.) and "Ceramer" (tradename, produced by Hoechst AG.) were used as the phenol resin-calcined product and polyphenylene sulfone resin, respectively.

Table 5

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 1	73	Baryte type	15	Calcium pyrophosphate	10
Example 2	72.5	Baryte type	15	Calcium pyrophosphate	10
Example 3	72.5	Baryte type	15	Calcium hydrogen phosphate	10
Example 4	69.5	Baryte type	18	Calcium pyrophosphate	10

Table 5 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 1	Thermosetting	2	-	-
Example 2	Thermosetting	2	Graphite	0.5
Example 3	Thermosetting	2	Graphite	0.5
Example 4	Thermosetting	2	Graphite	0.5

Table 5 (continued)

Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 1	11.5	5	7	14
Example 2	11	4	7	12
Example 3	13	8	8.5	16
Example 4	12	5	7.5	12

Table 6

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 5	69	Baryte type	18	Calcium hydrogen phosphate	10
Example 6	69	Precipitated type	18	Calcium pyrophosphate	10
Example 7	72	Baryte type	20	Calcium pyrophosphate	5
Example 8	71.5	Baryte type	20	Calcium pyrophosphate	5

Table 6 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 5	Thermosetting	2.5	Graphite	0.5
Example 6	Thermosetting	2.5	Molybdenum disulfide	0.5
Example 7	Thermosetting	3	-	-
Example 8	Thermosetting	3	Graphite	0.5

Table 6 (continued)

Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 5	14	5	7.5	12
Example 6	15	6	8	14
Example 7	15	4	9	17
Example 8	13	4	8	13

Table 7

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 9	68	Baryte type	20	Calcium pyro-phosphate	10
Example 10	67.5	Baryte type	20	Calcium pyro-phosphate	10
Example 11	67.5	Baryte type	20	Calcium hydrogen phosphate	10
Example 12	65	Baryte type	20	Calcium pyro-phosphate	10

Table 7 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 9	Thermosetting	2	-	-
Example 10	Aromatic	2	Graphite	0.5
Example 11	Aromatic	2	Molybdenum disulfide	0.5
Example 12	Thermosetting	4	Graphite	1

Table 7 (continued)

Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 9	14	3	7.5	13
Example 10	12	5	7.5	13
Example 11	13	6	8	15
Example 12	14	4	7.5	10

Table 8

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 13	67	Baryte type	25	Calcium pyro-phosphate	5
Example 14	66	Baryte type	25	Calcium pyro-phosphate	5
Example 15	62	Baryte type	25	Calcium pyro-phosphate	10

Table 8 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 13	Thermosetting	3	-	-
Example 14	Thermosetting	3	Graphite	1
Example 15	Thermosetting	3	-	-

Table 8 (continued)

Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 13	14	3	8.5	16
Example 14	16	6	8	14
Example 15	15	2	9	9

Table 9

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 16	70	Baryte type	15	Calcium pyro-phosphate	10
Example 17	69	Baryte type	15	Calcium pyro-phosphate	10
Example 18	68	Baryte type	18	Calcium pyro-phosphate	10
Example 19	67.5	Baryte type	18	Calcium pyro-phosphate	10
Example 20	70.5	Baryte type	15	Calcium pyro-phosphate	10

Table 9 (continued)

Examples	Polyimide		Phenol resin-calcined product
	Kind	Amount	
Example 16	-	-	5
Example 17	-	-	5
Example 18	-	-	-
Example 19	-	-	-
Example 20	Thermosetting	2	-

Table 9 (continued)

Examples	Polyphenylene sulfone resin	Solid lubricant	
		Kind	Amount
Example 16	-	-	-
Example 17	-	Graphite	1
Example 18	4	-	-
Example 19	4	Graphite	0.5
Example 20	2	Graphite	0.5

Table 9 (continued)

Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 16	12	3	7	17
Example 17	12	3	7	16
Example 18	13	4	8	13
Example 19	12	3	7	12
Example 20	13	4	9	13

Table 10

Comparative Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Comparative Example 1	50	-	-	-	-
Comparative Example 2	70	-	-	Calcium pyrophosphate	10
Comparative Example 3	80	-	-	-	-

Table 10 (continued)

Comparative Examples	Polyimide		Lead
	Kind	Amount	
Comparative Example 1	-	-	50
Comparative Example 2	-	-	20
Comparative Example 3	Aromatic	20	-

Table 10 (continued)

Comparative Examples	Thrust test (1)		Thrust test (2)	
	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Comparative Example 1	14	31	*	*
Comparative Example 2	16	8	11	85
Comparative Example 3	19	12	10	20

(Note) *: The friction coefficient of the test piece was abruptly increased two hours after starting the test and, therefore, the test was discontinued.

[0061] From the above test results, it was confirmed that- the multi-layered sliding members obtained in Examples exhibited a stable performance, a small wear amount and, therefore, excellent sliding characteristics through the test period. On the other hand, the multi-layered sliding members obtained in Comparative Examples, especially Comparative Examples 2 and 3, exhibited friction coefficients which are not so different from those of the multi-layered sliding

EP 1 132 634 A2

members obtained in Examples, but were large in wear amount and, therefore, deteriorated in sliding characteristics.

[0062] Then, the multi-layered plates obtained in Examples 1-2, 4, 7-10, 12-14 and 16-20, and Comparative Examples 2 and 3 were cut into small plates, and each small plate was bent into a semi-cylindrical shape while facing the coating layer inward, thereby obtaining a multi-layered sliding member having a radius of 20.0 mm, a length of 20.0 mm and a thickness of 1.05 mm as a test piece.

[0063] The results of the reciprocating slide tests (3) and (4) of the respective multi-layered sliding members are shown in Tables 11 to 14.

Table 11

Examples	Reciprocating test (3)		Reciprocating test (4)	
	Friction coefficient (x 10 ⁻³)	Wear amount (μm)	Friction coefficient (x 10 ⁻³)	Wear amount (μm)
Example 1	26	6	36	8
Example 2	24	5	35	5
Example 4	20	2	26	4
Example 7	26	4	30	6
Example 8	25	3	28	5

Table 12

Examples	Reciprocating test (3)		Reciprocating test (4)	
	Friction coefficient (x 10 ⁻³)	Wear amount (μm)	Friction coefficient (x 10 ⁻³)	Wear amount (μm)
Example 9	21	2	29	4
Example 10	23	3	28	4
Example 12	25	5	30	6
Example 13	28	5	33	6
Example 14	26	4	30	5

Table 13

Examples	Reciprocating test (3)		Reciprocating test (4)	
	Friction coefficient (x 10 ⁻³)	Wear amount (μm)	Friction coefficient (x 10 ⁻³)	Wear amount (μm)
Example 16	31	4	35	6
Example 17	29	4	38	6
Example 18	27	3	30	5
Example 19	28	4	33	3
Example 20	27	3	32	5

Table 14

Comparative Examples	Reciprocating test (3)		Reciprocating test (4)	
	Friction coefficient (x 10 ⁻³)	Wear amount (μm)	Friction coefficient (x 10 ⁻³)	Wear amount (μm)
Comparative Example 2	100	48	*	*
Comparative Example 3	28	7	51	18

(Note) *: The friction coefficient of the test piece was abruptly increased 30 minutes after starting the test and, therefore, the test was discontinued.

[0064] From the above test results, it was confirmed that the multi-layered sliding members obtained in Examples stably exhibited an extremely low friction coefficients as well as a small wear amount throughout the test period.

Examples 21 to 33 and Comparative Examples 4 to 6:

[0065] In the following examples and comparative examples, "Polyflon F201" (tradename, produced by Daikin Kogyo Co., Ltd) was used as the PTFE resin, and a mixed solvent of an aliphatic solvent and a naphthenic solvent "Exxsol" (tradename, produced by Exxon Chemical Co., Ltd) was used as the petroleum-based solvent.

[0066] First, the PTFE resin and the fillers shown in Tables 15 to 18 were charged into a Henschel mixer, and mixed under stirring. 20 parts by weight of the petroleum-based solvent was blended with 100 parts by weight of the resultant mixture, and mixed at a temperature (15°C) lower than the room-temperature transition point of the PTFE resin, to obtain a resin composition.

[0067] A phosphor bronze plate having a thickness of 0.3 mm was processed into an expanded metal provided with regularly arranged rectangular meshes each having a side (strand) length of 0.6 mm, and a thickness of 0.43 mm, thereby obtaining a substrate A. Also, fine metal wires made of phosphor bronze as warp and weft having a diameter of 0.3 mm were woven into a wire mesh with 50 meshes, thereby obtaining a substrate B.

[0068] The resin composition was applied over the substrate A made of the expanded metal and the substrate B made of the woven wire mesh, and rolled to fill the meshes of the metal mesh with the resin composition and cover the surface of the metal mesh therewith to form a coating layer composed of the resin composition thereon. The substrate obtained by filling the meshes and coating the surface with the resin composition was then held in a hot-air drying furnace heated to 220°C for 5 minutes to remove the solvent from the resin composition.

[0069] Then, thus dried substrates which had been obtained by filling the meshes and coating the surface with the resin composition was introduced into a heating furnace, and heated at 360°C for ten minutes to sinter the resin composition, and then rolled under pressure to correct the size, waviness and the like, thereby obtaining the substrate having a resin composition layer with a thickness of 0.13 mm on the surface thereof. After completion of the correction, the obtained sliding member material was cut into a rectangular sliding member having a size of 30 x 30 mm as a test piece.

[0070] Fig. 2 shows a plan view of the expanded metal, and Fig. 3 shows a cross-sectional view of the sliding member using the expanded metal shown in Fig. 2 as substrate. In Figs. 2 and 3, reference numeral 4 denotes the expanded metal; 5 denotes each side (strand); 6 denotes the mesh; and 7 denotes the coating layer (sliding layer) made of the resin composition which was filled in each mesh of the expanded metal and coated (covered) on the surface thereof.

[0071] In addition, Fig. 4 shows a cross-sectional view of the sliding member using the woven wire mesh as substrate. In Fig. 4, reference numeral 8 denotes the woven wire mesh; and 9 denotes the coating layer (sliding layer) made of the resin composition which was filled in each mesh of the woven wire mesh and coated (covered) on the surface thereof.

[0072] The results of the thrust test (2) for each sliding member are shown in Tables 15 to 18.

[0073] In the Tables, the amounts of respective components blended are expressed by "% by weight". Further, "Bellpearl C-2000" (tradename, produced by Kanebo Co., Ltd.) and "Ceramer" (tradename, produced by Hoechst AG.) were used as the phenol resin-calcined product and polyphenylene sulfone resin, respectively.

Table 15

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 21	73	Baryte type	15	Calcium pyro-phosphate	10
Example 22	73	Baryte type	15	Calcium pyro-phosphate	10
Example 23	69.5	Baryte type	18	Calcium pyro-phosphate	10
Example 24	69.5	Baryte type	18	Calcium pyro-phosphate	10

Table 15 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 21	Thermosetting	2	-	-
Example 22	Thermosetting	2	-	-
Example 23	Thermosetting	2	Graphite	0.5
Example 24	Thermosetting	2	Graphite	0.5

Table 15 (continued)

Examples	Substrate		Thrust test (2)	
	Kind		Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 21	A		7	12
Example 22	B		7	13
Example 23	A		7	11
Example 24	B		8	12

Table 16

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 25	68	Baryte type	20	Calcium pyro-phosphate	10
Example 26	67.5	Baryte type	20	Calcium pyro-phosphate	10
Example 27	66	Baryte type	20	Calcium pyro-phosphate	10
Example 28	62	Baryte type	25	Calcium pyro-phosphate	10

Table 16 (continued)

Examples	Polyimide		Solid lubricant	
	Kind	Amount	Kind	Amount
Example 25	Thermosetting	2	-	-
Example 26	Thermosetting	2	Graphite	0.5
Example 27	Thermosetting	4	-	-
Example 28	Thermosetting	3	-	-

Table 16 (continued)

Examples	Substrate	Thrust test (2)	
	Kind	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 25	A	8	13
Example 26	A	8	11
Example 27	A	9	10
Example 28	B	8	11

Table 17

Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Example 29	70	Baryte type	15	Calcium pyro-phosphate	10
Example 30	69	Baryte type	15	Calcium pyro-phosphate	10
Example 31	68	Baryte type	18	Calcium pyro-phosphate	10
Example 32	67.5	Baryte type	18	Calcium pyro-phosphate	10
Example 33	70.5	Baryte type	15	Calcium pyro-phosphate	10

Table 17 (continued)

Examples	Polyimide		Phenol resin-calcined product
	Kind	Amount	
Example 29	-	-	5
Example 30	-	-	5
Example 31	-	-	-
Example 32	-	-	-
Example 33	Thermosetting	2	-

Table 17 (continued)

Examples	Polyphenylene sulfone resin	Solid lubricant	
		Kind	Amount
Example 29	-	-	-
Example 30	-	Graphite	1
Example 31	4	-	-
Example 32	4	Graphite	0.5
Example 33	2	Graphite	0.5

Table 17 (continued)

Examples	Substrate	Thrust test (2)	
	Kind	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Example 29	A	7	15
Example 30	B	7	14
Example 31	B	8	13
Example 32	A	7	13
Example 33	A	9	13

Table 18

Comparative Examples	PTFE	Barium sulfate		Phosphate	
		Kind	Amount	Kind	Amount
Comparative Example 4	70	-	-	Calcium pyrophosphate	10
Comparative Example 5	70	-	-	Calcium pyrophosphate	10
Comparative Example 6	80	-	-	-	-

Table 18 (continued)

Comparative Examples	Polyimide		Lead
	Kind	Amount	
Comparative Example 4	-	-	20
Comparative Example 5	-	-	20
Comparative Example 6	Thermosetting	20	-

Table 18 (continued)

Comparative Examples	Substrate	Thrust test (2)	
	Kind	Friction coefficient ($\times 10^{-2}$)	Wear amount (μm)
Comparative Example 4	A	12	90
Comparative Example 5	B	13	96
Comparative Example 6	A	11	25

[0074] From the above test results, it was confirmed that- the sliding members obtained in Examples exhibited a low friction coefficients, a stable performance through the test period, and an extremely small wear amount of not more than 15 μm , and were, therefore, excellent in sliding characteristics. On the other hand, the sliding members obtained in Comparative Examples exhibited high friction coefficients and a large wear amount and were, therefore, deteriorated in sliding characteristics.

Claims

1. A resin composition for a sliding member comprising 5 to 40% by weight of barium sulfate; 1 to 30% by weight of

a phosphate; 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a polyphenylene sulfone resin; and the balance of a polytetrafluoroethylene resin.

2. A resin composition according to claim 1, wherein said polyimide resin is an aromatic polyimide resin and a thermosetting polyimide resin.

3. A resin composition according to claim 1, wherein said phosphate is a metal salt of diphosphoric acid, triphosphoric acid and pyrophosphoric acid.

4. A resin composition according to claim 3, wherein said phosphate is trillithium phosphate, lithium hydrogen phosphate, lithium pyrophosphate, tricalcium phosphate, calcium hydrogen phosphate and calcium pyrophosphate.

5. A resin composition according to claim 1, which further comprises graphite or molybdenum disulfide in an amount of not more than 5% by weight.

6. A sliding member comprising:

a substrate comprising a steel backing plate and a porous sintered metal layer formed on said steel backing plate, or comprising a metal mesh; and

a resin composition applied to pores or meshes and a surface of said substrate, comprising 5 to 40% by weight of barium sulfate, 1 to 30% by weight of a phosphate, 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a polyphenylene sulfone resin and the balance of a polytetrafluoroethylene resin.

7. A sliding member according to claim 6, wherein said polyimide resin is an aromatic polyimide resin and a thermosetting polyimide resin.

8. A sliding member according to claim 6, wherein said phosphate is a metal salt of diphosphoric acid, triphosphoric acid and pyrophosphoric acid.

9. A sliding member according to claim 8, wherein said phosphate is trillithium phosphate, lithium hydrogen phosphate, lithium pyrophosphate, tricalcium phosphate, calcium hydrogen phosphate and calcium pyrophosphate.

10. A sliding member according to claim 6, wherein said resin composition further contains graphite or molybdenum disulfide in an amount of not more than 5% by weight.

FIG.1




FIG.2




FIG.3





FIG.4



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 132 634 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
03.03.2004 Bulletin 2004/10

(51) Int Cl.7: **F16C 33/20**

(43) Date of publication A2:
12.09.2001 Bulletin 2001/37

(21) Application number: **00111970.0**

(22) Date of filing: **16.06.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Yanase, Sumihide**
Ebina-shi, Kanagawa-ken (JP)
• **Nakamaru, Takashi**
Alkou-gun, Kanagawa-ken (JP)

(30) Priority: **08.03.2000 JP 2000063838**

(74) Representative: **HOFFMANN - EITLE**
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(71) Applicant: **OILES CORPORATION**
Minato-ku, Tokyo (JP)


(54) **Resin composition for sliding member, and sliding member produced therefrom**

(57) A resin composition for a sliding member of the present invention comprises 5 to 40% by weight of barium sulfate; 1 to 30% by weight of a phosphate; 1 to 10% by weight of at least one selected from the group consisting of a polyimide resin, a phenol resin-calcined product and a polyphenylene sulfone resin; and the bal-

ance of a polytetrafluoroethylene resin, and a sliding member produced from the resin composition.

Such a resin composition suitable for producing a sliding member capable of exhibiting a stable low friction coefficient and an extremely low wear amount under dry frictional condition, or under oil-immersed or oil-lubricated condition.

FIG.1



EP 1 132 634 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 1970

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 232 922 A (KOLBENSCHMIDT AG) 19 August 1987 (1987-08-19) * the whole document *		F16C33/20
A	US 5 726 232 A (EGAMI MASAKI ET AL) 10 March 1998 (1998-03-10) * the whole document *		
A	DE 42 27 909 A (GLYCO METALL WERKE) 24 February 1994 (1994-02-24) * the whole document *		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			F16C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 14 January 2004	Examiner Leroy, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 1970

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

14-01-2004

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0232922	A	19-08-1987	DE	3601569 A1	23-07-1987
			AT	44080 T	15-06-1989
			DE	3760253 D1	20-07-1989
			EP	0232922 A1	19-08-1987
			JP	2747582 B2	06-05-1998
			JP	62184225 A	12-08-1987
			US	4847135 A	11-07-1989

US 5726232	A	10-03-1998	JP	8259765 A	08-10-1996

DE 4227909	A	24-02-1994	DE	4227909 A1	24-02-1994

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82